

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.

42  
B1

1. A method of extruding structural members comprising:
  - (a) providing an alloy comprising:
    - about 3.6 to about 4.2 wt.% copper,
    - about 1.0 to about 1.6 wt.% magnesium,
    - about 0.3 to about 0.8 wt.% manganese,
    - about 0.05 to about 0.25% zirconium,
    - the balance substantially aluminum, incidental elements and impurities;
  - (b) extruding said alloy within about 500° to about 750°F to form an extrusion;
  - (c) solution heat treating said extrusion; and
  - (d) quenching said extrusion before making a structural member therefrom.
2. The method of claim 1 wherein (b) is about 550° to about 650°F.
3. The method of claim 1 wherein (b) is about 600° to about 650°F.
4. The method of claim 1 which further includes:
  - (e) stretching said extrusion by at least about 1%.

5. The method of claim 1 which further includes:

(e) stretching said extrusion between about 1 to about 10%.

6. The method of claim 1 which further includes:

(e) stretching said extrusion between about 1 to about 8%.

7. The method of claim 1 which further includes:

(e) stretching said extrusion between about 1 to about 3%.

8. The method of claim 1 which further includes:

(e) stretching said extrusion by at least about 1%, said extrusion having less than about 50% by volume recrystallized after stretching.

9. The method of claim 1 which further includes:

(e) stretching said extrusion by at least about 1%, said extrusion being substantially unrecrystallized.

10. The method of claim 1 which further includes:

(e) stretching said extrusion by at least about 1%; said extrusion having a longitudinal yield strength of at least about 50 ksi and a longitudinal tensile ultimate strength of at least about 70 ksi.

11. A substantially unrecrystallized extrusion comprising:  
about 3.6 to about 4.2 wt.% copper,  
about 1.0 to about 1.6 wt.% magnesium,  
about 0.3 to about 0.8 wt.% manganese,  
about 0.05 to about 0.25% zirconium,  
the balance substantially aluminum, incidental elements and  
impurities.

12. The substantially unrecrystallized extrusion of claim 11 wherein the  
alloy further includes not more than about 0.06% silicon and not more than about 0.08%  
iron.

13. The substantially unrecrystallized extrusion of claim 11 wherein the  
alloy includes about 3.7 to about 4.1 wt.% copper.

14. The substantially unrecrystallized extrusion of claim 11 wherein the  
alloy includes about 1.15 to about 1.5 wt.% magnesium.

15. The substantially unrecrystallized extrusion of claim 11 wherein the  
alloy includes about 0.5 to about 0.6 wt.% manganese.

16. The substantially unrecrystallized extrusion of claim 11 wherein the alloy includes about 0.09 to about 0.13% zirconium.

17. A substantially unrecrystallized extrusion comprising:  
about 3.6 to about 4.2 wt.% copper,  
about 1.0 to about 1.6 wt.% magnesium,  
about 0.3 to about 0.8 wt.% manganese,  
about 0.05 to about 0.25% zirconium,  
the balance substantially aluminum, incidental elements and  
impurities,  
said substantially unrecrystallized extrusion having a longitudinal yield strength of at least  
about 50 ksi and a longitudinal tensile ultimate strength of at least about 70 ksi.

18. The substantially unrecrystallized extrusion of claim 17 wherein the alloy further includes not more than about 0.06% silicon and not more than about 0.08% iron.

19. The substantially unrecrystallized extrusion of claim 17 wherein the alloy includes about 3.7 to about 4.1 wt.% copper.

20. The substantially unrecrystallized extrusion of claim 17 wherein the alloy includes about 1.15 to about 1.5 wt.% magnesium.

21. The substantially unrecrystallized extrusion of claim 17 wherein the alloy includes about 0.5 to about 0.6 wt.% manganese.

22. The substantially unrecrystallized extrusion of claim 17 wherein the alloy further includes about 0.09 to about 0.13% zirconium.

23. The substantially unrecrystallized extrusion of claim 17 wherein the alloy further includes less than about 1.5 vol.% of Fe, Si, Mg, Mn and Cu bearing intermetallic particles.

24. A substantially unrecrystallized aircraft component comprising:  
about 3.6 to about 4.2 wt.% copper,  
about 1.0 to about 1.6 wt.% magnesium,  
about 0.3 to about 0.8 wt.% manganese,  
about 0.05 to about 0.25% zirconium,  
the balance substantially aluminum, incidental elements and  
impurities.

25. The substantially unrecrystallized aircraft component of claim 24 wherein the component is an aircraft fuselage component.

26. The substantially unrecrystallized aircraft component of claim 24 wherein the component is an aircraft wing stringer component.

1d  
B2 7